

Abstract

In an interdental brush, the filaments are retained between two wire sections (1a, 1b) which are twisted with one another. The wire sections (1a, 1b) have a diameter (D) of 0.3 mm or less and consist of a nickel-free or low-nickel steel. These brushes are distinguished by an increased level of rigidity and an improved restoring force and are stable even if the wire has a small diameter.

(Figure 2)